

Information + Instructions

Plaster for casts Art.: 900362

Usage:

For casting models and for creating negative and positive moulds. Also suitable for high-temperature use/hot foaming method.

Safety Precautions:

Protect from humidity – store in a cool and dry place.

Procedure:

Mixing ratio:	100g plaster: 30 ml water
Steeping time:	approximately 30 seconds
Setting time:	approximately 10 minutes

Expansion after 2 hours less than 0,18 %

Compression strength after 24 hours more than 40 N/square mm.

Tips and tricks:

To create a model plaster head:

If you add wood-glue (Ponal) and sawdust your model head will be easier to handle during further preparation.

e.g.

Using 3 litres of water, add 2 tablespoons of wood glue and then 2 handfuls of fine sawdust. Leave for approximately ½ an hour to allow absorption of the water, then add plaster as usual.

Our specialist Florian Schmidt-André will gladly provide further advice on usage at any time.